SPECIFICATION

SINGLE MODE OPTICAL FIBER WITH ELECTRON VACANCIES

5   TECHNICAL FIELD

The present invention relates to a single mode fiber
suitable for high-speed, large-capacity optical
communication and optical wiring, and particularly to a
10   hole-assisted single mode optical fiber.

BACKGROUND ART

Long-distance and large-capacity optical
15   communication using optical amplification technique has
a problem of degradation in transmission characteristics
due to optical nonlinear phenomena in single mode fibers.
The optical nonlinearity in a single mode fiber varies
in proportion to a nonlinear coefficient n2/Aeff obtained
20   by dividing a nonlinear refractive index n2 by an effective
cross-sectional area Aeff (G. P. Agrawal, "Nonlinear Fiber
Optics (second edition)", Academic Press, 1995,
particularly refer to section 2.3.1, p. 42). Accordingly,
the degradation in the transmission characteristics due
25   to the optical nonlinear phenomena in the long-distance
and large-capacity optical communication can be reduced
by decreasing the nonlinear coefficient in the single mode

- 1 -

fiber by increasing the effective cross-sectional area Aeff of the single mode fiber.

Thus, as for the conventional single mode fibers, attempts have been made to increase the effective cross-sectional area Aeff in the design and optimization of the refractive index profile forming the optical waveguide structure. Up to this time, in an operating wavelength region from about 1310 nm to 1625 nm, characteristics of single mode fibers with the effective cross-sectional area Aeff of about 70 μm^2 to 150 μm^2 have been disclosed (see, Japanese Patent Application Laid-open No. 9-274118 (1997) (Claim 6), Japanese Patent Application Laid-open No. 11-218632 (1999) (Claim 1), Japanese Patent Application Laid-open No. 2001-033647 (Claim 1 and a representative drawing Fig. 1), and Japanese Patent Application Laid-open No. 2001-147338 (Claim 13, paragraph [0022]), for example).

On the other hand, as for conventional 1.3 μm-band zero dispersion single mode fibers, they can be implemented with a simple two layer structure including a core region with a higher refractive index and a cladding region with a lower refractive index than the core region. Since they have a comparatively large effective cross-sectional area Aeff of about 80 μm^2 near the wavelength 1550 nm, they can achieve good connection and handling characteristics, and have been widely used in the optical communication and optical wiring until now.

The increase in the effective cross-sectional area Aeff in the design and optimization of the refractive index profile, however, will generally complicate the refractive index profile in the radial direction in a cross section

5   of a single mode fiber (SMF). In addition, in the SMF whose effective cross-sectional area Aeff is increased, the optical confinement of the light propagating through the optical fiber within the optical core reduces, and the bending loss characteristic is deteriorated. This offers

10   a problem in that the actual value of the feasible effective cross-sectional area Aeff is limited to a region in which the acceptable bending loss characteristic is achieved. For example, the bending loss at the bending radius 10 mm is limited to a range from 10 dB/m to 100 dB/m or less.

15   In addition, as for the SMF whose effective cross-sectional area Aeff is increased, the theoretical cutoff wavelength in the fundamental LP_{11} mode has a tendency to shift to a longer wavelength region. This presents a problem in that the effective operating wavelength region

20   is limited to a longer wavelength region of 1400 nm or more, for example (refer to Japanese Patent Application Laid-open No. 2001-147338 (Claim 13 and paragraph [0022], for example).

Furthermore, although the conventional SMF has a simple

25   structure and comparatively large effective cross-sectional area Aeff, its adaptive or applicable area is limited to a region in which the bending radius is

comparatively large such as from 20 mm to 30 mm because of the degradation in the bending loss characteristics. Accordingly, it has a drawback of being unable to make compact in actual optical transmission paths or optical wiring

5   because the wiring or storage space is limited in accordance with the acceptable bending radius. Thus, to improve the bending loss characteristic of the conventional SMF, some SMFs provided for reduction of mode field diameter (MFD) have been developed. However, the SMFs of this type have

10 a problem of impairing the handling characteristics such as the splice loss as a result of the reduction in the MFD.

DISCLOSURE OF THE INVENTION

15   The present invention is implemented to solve the foregoing problems. Therefore it is an object of the present invention to provide a hole-assisted single mode optical fiber that has in an operating wavelength region from 1260 nm to 1625 nm the effective cross-sectional area

20 Aeff equal to or greater than 150 μm^2 and the bending loss characteristic equal to or less than 1 dB/m at the bending radius 10 mm, and to provide a hole-assisted single mode optical fiber that has the bending loss equal to or less than 1 dB/m at the bending radius 10 mm and the mode field

25 diameter (MFD) from 7.9 μm to 10.2 μm at the wavelength 1310 nm (refer to ITU-T, recommendation G.652 (Table 1/G.652, p.6 of Revised Version in October, 2000), which is equivalent

to the MFD of the conventional 1.3 μm-band zero dispersion single mode fiber (SMF).

The hole-assisted single mode optical fiber in accordance with the present invention solves the problems

5   by comprising a first cladding region (11) with a uniform refractive index, a core region (10) with a refractive index higher than that of the first cladding region, and a second cladding region composed of a plurality of air hole regions (12) placed in the first cladding region in the surrounding

10   region of the core region; by optimizing the radius r2 of the air hole regions and the distance d of the air hole regions from a center of the core region; and farther by optimizing the relative index difference Δ between the core region and the first cladding region and the core radius

15   r1.

More specifically, to accomplish the foregoing objects, according to the present invention, there is provided a hole-assisted single mode optical fiber comprising: a first cladding region (11) having a uniform refractive index;

20   a core region (10) with a radius r1 having a refractive index higher than that of the first cladding region (11), and placed at a center of the first cladding region (11); and a second cladding region including at least four air hole regions (12), each of which has a radius r2, is separated

25   by a distance d from a center of the core region (10), and is placed in the first cladding region (11), wherein the distance d is 2.0 to 4.5 times the radius r1 of the core

- 5 -

region (10), and the radius r2 of the air hole regions (12) is equal to or greater than 0.2 times the radius r1 of the core region.

The radius r1 of the core region (10) can be from 3.2 μm to 4.8 μm, and a relative index difference Δ of the core region (10) from the first cladding region (11) can be in a range from 0.3% to 0.55%.

The mode field diameter at a wavelength 1310 nm can be from 7.9 μm to 10.2 μm.

The relative index difference Δ of the core region (10) from the first cladding region (11) can be equal to or less than 0.12%, and the effective core radius A from the center of the core region (10) to the extreme circumference of the air hole regions (12) can be in a range from 23 μm to 28 μm.

According to the present invention, it becomes possible to satisfy all the characteristics of the bending loss equal to or less than 1 dB/m at the bending radius 10 mm, and the effective cross-sectional area Aeff equal to or greater than 150 μm^2 in a region in which the theoretical cutoff wavelength in the fundamental LP_{11} mode is equal to or less than 1500 nm and the operating wavelength is from 1260 nm to 1625 nm, for example, by providing, in addition to the core region and first cladding region having the same refractive index gradient as that of a conventional single mode fiber, the second cladding region having at least four air hole regions within the first cladding region, and by

optimizing the core radius r1, the relative index difference
Δ of the core region, the air hole radius r2, and the distance
d of the air hole regions, thereby offering a marked advantage
of being able to implement the reduction in the optical
5   nonlinearity in a wide single mode operation region.

In addition, according to the present invention, it
also becomes possible for the single mode fiber with the
same structure as described above to satisfy the theoretical
cutoff wavelength in the fundamental LP_{11} mode equal to or
10   less than 1500 nm and the bending loss equal to or less
than 1 dB/m at the bending radius 10 mm in the operating
wavelength region from 1260 nm to 1625 nm, and to implement
high bending loss resistance, to keep the MFD
characteristics equivalent to that of the conventional SMF
15   at the wavelength 1310 nm, and to make the variations in
the MFD with reference to the conventional SMF equal to
or less than $\pm 10\%$ even at the wavelength 1625 nm, thereby
offering an advantage of being able to achieve good
connection characteristics with the conventional SMF.
20   Furthermore, since the single mode fiber in accordance
with the present invention has a structure that provides
many air hole regions to a single mode fiber with a prescribed
refractive index profile, it can be fabricated
comparatively easier than this type of conventional single
25   mode fiber.

BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1A-1C are schematic cross-sectional views each showing a cross-sectional structure of a single mode fiber of an embodiment in accordance with the present invention, Fig. 1A shows an example with four air holes, Fig. 1B shows an example with six air holes, and Fig. 1C shows an example with eight air holes;

Fig. 2 is a characteristic diagram illustrating relationships between the relative index difference Δ and the core radius r1 in a conventional 1.3 μm -band zero dispersion single mode fiber, which are determined by requirements of the zero dispersion wavelength, cutoff wavelength, and bending loss characteristic;

Figs. 3A-3C are characteristic diagrams each illustrating relationships between the normalized air hole distance d/r1 and the bending loss of a hole-assisted single mode optical fiber in an embodiment in accordance with the present invention, Fig. 3A shows an example with four air holes, Fig. 3B shows an example with six air holes, and Fig. 3C shows an example with eight air holes;

Fig. 4 is a characteristic diagram illustrating relationships between the normalized air hole distance d/r1 and the theoretical cutoff wavelength in the fundamental LP_{11} mode of a hole-assisted single mode optical fiber of a first embodiment in accordance with the present invention;

Fig. 5 is a characteristic diagram illustrating

variations in the MFD versus normalized air hole distance d/r1 at the wavelength 1310 nm of the hole-assisted single mode optical fiber in the first embodiment in accordance with the present invention;

5   Fig. 6 is a characteristic diagram illustrating relationships of the relative variations in the MFD and of the splice loss due to the mismatch of the MFD with reference to a conventional SMF versus normalized air hole distance d/r1 at the wavelength 1625 nm of the hole-assisted

10   single mode optical fiber of the first embodiment in accordance with the present invention;

Fig. 7 is a characteristic diagram illustrating measurement results of the wavelength characteristics of the bending loss in the hole-assisted single mode optical

15   fiber with six air holes fabricated according to the first embodiment in accordance with the present invention;

Fig. 8 is a characteristic diagram illustrating relationships between the relative index difference Δ in the core region and the effective core radius A of a

20   hole-assisted single mode optical fiber in a second embodiment in accordance with the present invention;

Fig. 9 is a characteristic diagram illustrating relationships between the relative index difference Δ in the core region and the effective cross-sectional area Aeff

25   of the hole-assisted single mode optical fiber in the second embodiment in accordance with the present invention; and

Fig. 10 is a characteristic diagram illustrating

relationships between the relative index difference Δ in the core region and the theoretical cutoff wavelength in the fundamental LP_{11} mode of the hole-assisted single mode optical fiber in the second embodiment in accordance with

5   the present invention.

BEST MODE FOR CARRYING OUT THE INVENTION

The best mode for carrying out the invention will now

10   be described with reference to the accompanying drawings.
FIRST EMBODIMENTF

Figs. 1A-1C are schematic cross-sectional views each showing a cross-sectional structure of an embodiment of a hole-assisted single mode optical fiber in accordance

15   with the present invention: Fig. 1A shows an example with four air holes; Fig. 1B shows an example with six air holes; and Fig. 1C shows an example with eight air holes.

The single mode fiber in accordance with the present invention comprises a core region 10 with a radius r1, a

20   first cladding region 11 that surrounds the core region and has a uniform refractive index, and a second cladding region including at least four air hole regions 12 that are placed at a distance d from the center of the core region 10 and have a radius r2.   It is assumed that the air hole

25   regions 12 are each formed in the longitudinal direction of the optical fiber, and are disposed separately at fixed same interval in a cross section of the optical fiber, and

that their diameters are substantially constant in average throughout the longitudinal direction of the optical fiber.

The refractive index n1 of the core region 10 is adjusted by the dopant material and amount of the dopant such that the refractive index n1 becomes higher than the refractive index n2 of the first cladding region 11 as in the conventional single mode fiber. Thus, the core region 10 and first cladding region 11 constitute the major optical waveguide structure. As for the refractive index profile of the core region 10, any types of the refractive index profile as in the conventional single mode fiber are applicable.

In the embodiment in accordance with the present invention, the characteristics of the hole-assisted single mode optical fiber with a step refractive index profile will be described which is formed by setting the refractive index of the first cladding region 11 at a pure silica (SiO_2) level, by placing the refractive index of the second cladding region at one (air), and by doping germanium into the core region 10. Incidentally, it is also possible to design the refractive index of the core region 10 equal to or less than the refractive index of pure silica by making the refractive index of the first cladding region 11 less than that of the pure silica by doping fluorine or the like.

First, the first embodiment in accordance with the present invention will now be described by way of example which is designed in such a manner that the radius of the

core region 10 (called "core radius" from now on) r1 and

the relative index difference Δ of the core region 10 with

respect to the first cladding region 11 each satisfy the

characteristics of the conventional 1.3 μm-band zero

5   dispersion single mode fiber (SMF).

Fig. 2 is a characteristic diagram illustrating

relationships between the relative index difference Δ and

the core radius r1 (design range) in a conventional SMF,

which are determined by requirements of the zero dispersion

10   wavelength, cutoff wavelength, and bending loss

characteristic (refer to ITU-T, recommendation G.652 (Table

1/G.652, p.6 of Revised Version in October, 2000). The

design range is indicated as a dotted area in Fig. 2. Here,

the relative index difference Δ (%) is designed by the

15   following expression (1) using the refractive index n1 of

the core region 10 and the refractive index n2 of the cladding

region (the first cladding region 11 in the structure in

accordance with the present invention).

20   $$\Delta = \frac{n1^2 - n2^2}{2n1^2} \times 100 \qquad (1)$$

Fig. 2 shows that the requirements of the conventional

SMF can be satisfied by designing in such a manner that

the radius r1 of the core region 10 is in a range from about

25   3.2 μm to 4.8 μm, and the relative index difference Δ is

in a range from about 0.3% to 0.55%.

- 12 -

Figs. 3A-3C are characteristic diagrams illustrating relationships between the normalized air hole distance d/r1 and the bending loss characteristic at the bending radius 10 mm at wavelength 1625 nm using the radius of the air hole regions (called "air hole radius" from now on) r2 as a parameter. In the example of Figs. 3A-3C, the relative index difference Δ is made 0.32%, and r1 is made 4.5 μm from the relationships as illustrated in Fig. 2.

Here, Fig. 3A shows a characteristic example in which the number of the air hole regions 12 (called "air hole number" from now on) is four, Fig. 3B shows a characteristic example with six air holes, and Fig. 3C shows a characteristic example with eight air holes.

Generally, the mode field diameter (MFD) of the single mode fiber increases more and more in the longer wavelength region, and in connection with this, the bending loss characteristic tends to degrade in the longer wavelength region. Accordingly, in the hole-assisted single mode optical fiber with the number of air holes being four, six or eight as shown in Figs. 3A-3C, the bending loss characteristic at the bending radius 10 mm can be made equal to or less than 1 dB/m in a wavelength range equal to or less than 1625 nm by making the design within the parameters of the air hole radius r2 is about 0.2 times the core radius r1 or more, and the air hole distance d is about 4.5 times the core radius r1 or less.

Fig. 4 is a diagram illustrating relationships between

the normalized air hole distance d/r1 and the theoretical cutoff wavelength in the fundamental LP_{11} mode of a hole-assisted single mode optical fiber in which the number of air holes is eight, and the air hole radius r2 is 0.4

5   times the core radius r1.   The theoretical cutoff wavelength in the fundamental LP_{11} mode of the foregoing conventional SMF whose relative index difference Δ is 0.32% and the core radius r1 is 4.5 μm is about 1450 nm.   The hole-assisted single mode optical fiber in accordance with the present

10   invention can also achieve the cutoff wavelength characteristic equivalent to that of the conventional SMF or less as illustrated in Fig. 4.

Fig. 5 is a diagram illustrating variations in the MFD (mode field diameter) versus the normalized air hole

15   distance d/r1 at the wavelength 1310 nm of the hole-assisted single mode optical fiber with the same conditions as those shown in Fig. 4 in the number of air holes and all.   As illustrated in Fig. 5, the optical fiber can achieve the MFD characteristic from about 7.9 μm to 10.2 μm, which is

20   equivalent to that of the conventional SMF, by making the design in the range in which the normalized air hole distance d/r1 is about 1.5 or more.

Fig. 6 is a characteristic diagram illustrating relative variations in the present MFD of the hole-assisted

25   single mode optical fiber with reference to the MFD of the conventional SMF and the splice loss due to the mismatch of the MFD versus the normalized air hole distance d/r1

- 14 -

at the wavelength 1625 nm. Here, the solid curve represents
the characteristics of the relative variations in the MFD,
and the dotted curve represents the characteristics of the
MFD mismatch loss. As illustrated in Fig. 6, making the
5   design in the range in which the normalized air hole distance
d/r1 is 2.0 or more enables the relative variations in the
MFD involved in providing the air hole regions 12 to be
equal to or less than ±10% with reference to the MFD of
the conventional SMF at the wavelength 1625 nm, and to enable
10   the splice loss due to the mismatch of the MFD to be less
than 1 dB.

Therefore, it is possible to achieve the
characteristics that enable the relative variations in the
present MFD with reference to the MFD of the conventional
15   SMF to be curbed equal to or less than ±10% even at the
upper limit 1625 nm of the operating wavelength by making
the theoretical cutoff wavelength in the fundamental LP_{11}
mode equal to or less than 1500 nm, by making the bending
loss characteristic at the bending radius 10 mm equal to
20   or less than 1 dB/m in the operating wavelength region from
1260 nm to 1625 nm, and by making the MFD at the wavelength
1310 nm from about 7.9 μm to 10.2 μm which is equivalent
to that of the conventional SMF by making the design of
the hole-assisted single mode optical fiber in accordance
25   with the present invention, which has at least four air
hole regions 12 as shown in Figs. 2, 3A-3C, 4, 5 and 6,
in the range in which the distance d of the air hole regions

12 is 2.0 - 4.5 times the core radius r1, the radius r2 of the air hole regions 12 is 0.2 times the core radius r1 or more, the relative index difference Δ of the core region 10 is about 0.3% to 0.55%, and the core radius r1 is about 3.2 μm to 4.8 μm.

Fig. 7 is a diagram illustrating measurement results of the wavelength characteristics of the bending loss in two types of hole-assisted single mode optical fibers with six air hole regions 12 which were fabricated experimentally on the basis of the embodiment in accordance with the present invention in comparison with the conventional SMF. The measurement conditions of the bending loss were that the bending radius was 10 mm with 20 turns. In Fig. 7, solid circles represent the characteristics of the conventional SMF, and circles with X represent the characteristics of the hole-assisted SMF in accordance with the present invention. The bending loss of the prototype hole-assisted single mode optical fiber in the measurement wavelength region is equal to or less than measurement minimum limit of 0.01 dB/m. In particular, the bending loss reduction effect of two orders of magnitude higher than the conventional SMF is achieved in the longer wavelength region.

SECOND EMBODIMENT

Next, as the second embodiment in accordance with the present invention, an example will be described in which the effective cross-sectional area Aeff is increased by

optimizing the relative index difference Δ of the core region 10 and the core radius.

Fig. 8 is a diagram illustrating relationships between the relative index difference Δ of the core region 10 from the refractive index of the first cladding region 11 and the effective core radius A, in which the bending loss at the bending radius 10 mm is equal to or less than 1 dB/m. Here, the effective core radius A is defined as the distance from the center of the core region 10 to the extreme circumference of the second cladding region, which is equal to A = d + 2×r2 (see, Figs. 1A-1C). As an example, the number of the air hole regions 12 constituting the second cladding region is six, the air hole radius r2 is 0.3 times the core radius r1, and the air hole distance d is three times the core radius r1.

Fig. 8 shows that the bending loss at the bending radius 10 mm can be made equal to or less than 1 dB/m in the operating wavelength range from 1260 nm to 1625 nm by designing using the relationships between relative index difference Δ and the effective core radius A at the wavelength 1260 nm.

Fig. 9 is a diagram illustrating relationships between the relative index difference Δ of the core region 10 and the effective cross-sectional area Aeff at the wavelength 1260 nm, 1550 nm and 1625 nm when using the relationships between the relative index difference Δ and the effective core radius A at the wavelength 1260 nm of Fig. 8.

In addition, Fig. 10 is a diagram illustrating

relationships between the relative index difference Δ of the core region 10 and the theoretical cutoff wavelength in the fundamental LP_{11} mode when using the relationships between the relative index difference Δ and the effective core radius A at the wavelength 1260 nm of Fig. 8.

Therefore, as shown in Figs. 8, 9 and 10, it is possible for the second embodiment in accordance with the present invention, in the single mode fiber with six air hole regions 12 which are placed at the distance $d = 3 \times r1$ from the center of the core region 10 and have the radius $r2 = 0.3 \times r1$, to achieve the characteristics that enable the effective cross-sectional area Aeff in the wavelength range from 1260 nm to 1625 nm to be equal to or greater than 150 μm^2, and the bending loss at the bending radius 10 mm to be equal to or less than 1 dB/m by making the theoretical cutoff wavelength in the fundamental LP_{11} mode equal to or less than 1100 nm by making the design in the range in which the relative index difference Δ of the core region 10 is equal to or less than about 0.12%, and the effective core radius A is about from 23 μm to 28 μm.

OTHER EMBODIMENTS

Although the preferred embodiments in accordance with the present invention have been described by way of example, the embodiments in accordance with the present invention are not limited to the foregoing examples. As long as they are within the scope of appended claims, substitutes, modifications, revisions, additions, increase or decrease

of the number, and changes in shapes of the components all fall within the range of the embodiment in accordance with the present invention. For example, the number of the air hole regions 12, the materials of the optical fiber, and the like in accordance with the present invention are not limited to those described in the foregoing embodiments. The optical fiber can be formed not only by glass, but also by any transparent media in the used wavelength such as plastics. In addition, although the air hole regions 12 are preferably cylindrical, elliptical or polygonal holes very close to cylindrical holes are also applicable. Furthermore, the internal space of the air hole regions 12 is not limited to a vacuum. For example, they may be filled with a gas, liquid, or solid which is transparent at the used wavelength, and has a refractive index lower than that of the first cladding region 11.